

Seeflex 040E

SPECIFICATIONS

Physical Properties	
Hardness	90 Shore A
Wall Thickness	0,90 mm
Tensile Strength	40 MPa
Temp. Range(°C)	-25 to 110
Low Temp, Flexibility	Good
Surface Finish	Gloss/Gloss
Ultimate Elongation	450 %
Tear Strength (Die C)	67 kN/m
Material Resistance (Ohms)	10^{10}
100% Modulus	8 MPa
300% Modulus	12,6 MPa
Permeability	0



- Used on all types of stationary, vibratory & gyratory sifters, screeners, feeders, bin discharges, hoppers, conveyors, packing equipment or any product handling equipment
- Dust control sleeves and transitions, the 1st choice for dust free factories
- Superior chemical resistance for CIP and washing
- Excellent abrasion resistance
- Smooth welded seam

Seeflex 040E is a clear ether based thermoplastic polyurethane alloy. Having no memory Seeflex 040E will not fracture as a result of constant flexing.

Atex compliant on products as low as 10mJ

Complies with the following regulations:

FDA CFR 177.1680. & 177.2600

(EC) 1935/2004, 2023 -2006, 2002/72, 10/2011

USDA & 3A (20 -25)